

worldwide corrosion protection

CASE STUDY: DRINKING WATER TANK

LOCATION: MIDLANDS

MARKET: UTILITIES

REQUIREMENT:

Relining of a drinking water tank meeting the BS 6920:2000 standard for use in contact with potable water.

WRAS approved system. Approval Number1204534



Substrate Mild Steel.

Prepared using rust scrapers, chipping hammers, needle guns, wire brushes etc to St2 standard of EN ISO 8501-1:2007 or equivalent. All scale was removed. The surface was washed down with clean fresh water prior to application and allowed to dry.

COATINGS:

One coat of Corroless EPF and one coat Corroless RF35 (2006)1:2007 (with stripe coating where appropriate).

PRODUCT DFT

Corroless EPF Buff 200 microns Corroless RF35 (2006) Grey 200 microns

COMMENTS:

System has an expected life of 10 years in immersion conditions.







