

Corroless ACO Spray Grade

(formerly Acothane Spray Grade)

Product Description	A high build, solvent free, two pack polyurethane coating for spray application onto steel pipes and field joints.				
Features & Use	<ul style="list-style-type: none"> Outstanding physical properties in terms of flexural strength, tensile strength, impact and abrasion resistance Use for the protection of steel and concrete structures in aggressive environments e.g. internal and external protection of pipelines, field joints, offshore splash zones, bridge protection, chemical plants 				
Approvals/ Certification	<ul style="list-style-type: none"> Meets the requirements of GBE/CW6 Part 1 for External Pipe Protection Meets the performance requirements of BS EN 10290 and AWWA C222 Malaysian SPAN approved Approvals held in the former name of 'Acothane' 				
Finish	Sheen				
Volume Solids	100%				
VOC Content	0 g/litre				
Film Thickness Range And Coverage		Dry Film Thickness	Wet Film Thickness	Theoretical Coverage	
	Typical	0.5 mm	0.5 mm	2.0 m ² /litre	
	Typical	5 mm	5 mm	0.2 m ² /litre	
	Practical coverage depends on the application method, painting conditions and the shape and roughness of the surface to be coated				
Drying Times	Applied to 1 mm DFT	+10°C	+20°C	+30°C	+40°C
	Dust Free	50 min	30 min	15 min	10 min
	Hard Dry	8 hr	4 hr	3 hr	2 hr
	Stackable	16 hr	8 hr	7 hr	7 hr
	Full Cure	7 days	7 days	6 days	5 days
	Drying and recoating times are related to the surface temperature				
Colours	Cream, Grey and a limited range of other shades				
Mix Ratio/ Product Code	10SGR (base) and 10ACT (activator) Base 3 parts by volume 3.23 parts by Weight Hardener 1 part by volume 1 part by Weight				
Pot Life	5 min at 20°C				
SG	1.29 kg/lit mixed				
Storage Conditions	Store in dry, cool conditions and protect from frost				
Shelf Life	Minimum 24 months if stored as above in unopened containers				
Flash Point	Above 60°C				

Corroless ACO Spray Grade

Issue Date: Aug 2020
Page 2 of 2

Surface Preparation	<ul style="list-style-type: none"> All surfaces to be coated should be dry and cleaned as necessary to remove all oil, grease, salts, weld flux or other contamination. Where necessary, remove weld spatter and grind smooth all sharp edges and weld seams Steel: blast clean to minimum Sa2½ (ISO 8501-1:2007), surface profile depth 75-100µm. Mechanical tools may also be used providing a profile of minimum 75µm. <u>Do not polish the steel surface</u> Concrete: remove all laitance and other contaminants by most appropriate methods. Ensure the concrete is dry to a reading of <16% on the Wood Moisture Equivalent (WME) scale. Prime with Corroless ACO LV Sealer 														
Mixing	Twin feed equipment required														
Thinner / Cleaner	Do not thin / Axalta Thinner Fast Industrial TH120 (formerly called No.4 Thinner)														
Application Conditions	Do not apply when rain, mist, sleet or snow are imminent. Normal application requires relative humidity below 80%. To avoid risk of condensation, application should be performed only when the steel surface temperature is at least 3°C (5°F) above the dew point. Application at temperatures below 1°C (33°F) must be carefully monitored, since the possible presence of ice on the surface (or in pores, in the case of concrete) will result in poor performance.														
Application Methods	<table border="1"> <thead> <tr> <th>Method</th> <th>Airless Spray</th> <th>Conventional Spray</th> <th>Brush</th> <th>Roller</th> </tr> </thead> <tbody> <tr> <td colspan="5" style="text-align: center;">See below</td> </tr> </tbody> </table>	Method	Airless Spray	Conventional Spray	Brush	Roller	See below								
Method	Airless Spray	Conventional Spray	Brush	Roller											
See below															
<ul style="list-style-type: none"> Twin component hot airless spray required with instant purge capability due to very short pot life – please consult Axalta Coating Systems for advice Note that the use of the Sulzer cartridge spraying system or other low-pressure spraying systems is not permitted for Drinking water applications requiring WRAS approvals 															
Product Notes	<ul style="list-style-type: none"> Activator contains isocyanates – refer to Safety Data Sheet Overcoating - normally after 1 hour and within 24 hours of initial application. Abrading will be required if overcoating after 24 hours In-service temperature limits: Wet – 0°C to 70°C depending on solution; Dry – minus 20°C to + 120°C continuous Curing rate will be retarded below 10°C Backfilling or immersion can normally be carried out as soon as the coating is Hard Dry Spark/Holiday testing: maximum 5KV after the coating is hard dry Corroless ACO Spray Grade has excellent adhesion to abraded Fusion Bonded Epoxy (FBE), and suitably prepared 3LPE and 3LPP. Please consult Axalta Coating Systems for technical advice 														
Health & Safety	Containers are provided with safety labels which should be observed. Further information about hazardous influences and protection are detailed in individual Product Safety Data Sheets. A Safety Data Sheet for this product is available on request from Axalta Coating Systems.														

AN AXALTA COATING SYSTEMS BRAND



The information provided herein corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials or additives or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since Axalta cannot anticipate all variations in actual end-use conditions Axalta makes no warranties and assumes no liability in connection with any of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights. This product is for professional use only.