

Corroless CCI Powder

CORROSION INHIBITOR

| | |
|--|---|
| Product Description | A vapour phase corrosion inhibitor (VCI), offering a convenient and effective means of protecting against corrosion in enclosed areas. |
| Features & Use | <ul style="list-style-type: none"> • Subject to normal government restrictions, CCI Powder can be discharged into the marine environment • The powder can be blown into cavities and complex equipment where application of a conventional coating would not be possible • Offers multi metal protection • It is not usually necessary to remove the powder prior to commissioning equipment • Applications include cavity and void space protection, tanks, pipe internals, box sections, valves etc. |
| Approvals/ Certification | <ul style="list-style-type: none"> • Accepted onto the List for Approved Products suitable for use by the North Sea Oil and Gas industry, based on testing for its environmental impact • OCNS Registration Number 1413 |
| Finish | Not Applicable |
| Volume Solids | Not applicable |
| VOC Content | Not applicable |
| Film Thickness Range And Coverage | Not Applicable, see application details for treatment rates |
| Drying Times | Not Applicable, does not dry |
| Colours | White crystalline powder |
| Mix Ratio | Not applicable |
| Pot Life | Not applicable |
| SG | Not applicable |
| Storage Conditions | Store in dry, cool conditions and protect from frost |
| Shelf Life | Minimum 24 months if stored as above in unopened containers |
| Flash Point | Greater than 55°C |

Corroless CCI Powder

 Issue Date: June 2020
 Page 2 of 2

| | |
|-------------------------------|--|
| Surface Preparation | No surface preparation required. For best results remove any contamination, dirt, moisture or condensation prior to application |
| Mixing | Not Applicable |
| Thinners/Cleaner | Not applicable (Water may be used to clean up) |
| Application Conditions | <ul style="list-style-type: none"> Do not apply in temperatures below 0°C. Keep the powder dry and reseal any opened containers. Wet or damp powder will cake and will not disperse correctly During application the Relative Humidity should not exceed 85% and the steel temperature should remain at least 3°C above the Dew Point. |
| Application | <p>The quantity of CCI Powder required should be estimated from the air space to be protected:</p> <p>24 months protection 15 g/litre or 525 g/m³ 12 months protection 10 g/litre or 350 g/m³ 6 months protection 7 g/litre or 245 g/m³</p> <ul style="list-style-type: none"> The powder should be blown into the cavity or tank using bellows or low pressure compressed air, until all the powder is thoroughly dispersed within the void space Immediately after application all vents, doors, or openings should be sealed to create a contained system, to prevent loss of VCI vapour During application all vessels and plant, together with all application equipment, should be earthed and all possible ignition sources removed |
| Health & Safety | Containers are provided with safety labels which should be observed. Further information about hazardous influences and protection are detailed in individual Product Safety Data Sheets. A Safety Data Sheet for this product is available on request from Axalta Coating Systems. |

AN AXALTA COATING SYSTEMS BRAND



The information provided herein corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials or additives or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since Axalta cannot anticipate all variations in actual end-use conditions Axalta makes no warranties and assumes no liability in connection with any of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights. This product is for professional use only.