

Permacron[®] 1:1 Elastic Primer Surfacer 3300



GENERAL

DESCRIPTION

A universal 2K Primer Surfacer for all plastic parts commonly found on passenger vehicle exteriors.

This economical primer surfacer can be recoated directly with an elastic base coat. It is characterized by good adhesion, high elasticity, and easy application. Permacron® 1:1 Elastic Primer Surfacer 3300 is available in gray and black.

The products referenced herein may not be available for sale in your market. Please consult your distributor for product availability.



MIXING

COMPONENTS

Permacron 1:1 Elastic Primer Surfacer 3300

PERMACRON ELASTIC HARDENER

Permacron Elastic Hardener 3301

MIX RATIO

Component	Volume
3300	1
3301	1

APPLICATION VISCOSITY

Approximately 17 – 21 seconds at 68°F/20°C, DIN 4

POT LIFE

Approximately 8 hours at 68°F/20°C

SPECIAL TIPS

- Do not allow Permahyd[®] Plastic Cleaning Paste 7081 to dry on the surface of the plastic substrate.
- Thoroughly clean and scuff all surfaces of the plastic part, paying special attention to all edges.
- 3. For hard to reach areas of the plastic part, use the application brush that is included with the Permahyd Plastic Cleaning Paste 7081.
- Permahyd[®] Plastic Cleaning Paste 7081 is designed for raw plastic and is not suitable for cleaning painted surfaces.
- 5. Always use a clean scuff pad.
- 6. Soft plastic may require a finer scuff pad.
- 7. Difficult to clean plastics may need to be cleaned more times, or if applicable the plastic may be baked for a minimum of 15 minutes at 140°F (60°C). Some OEM plastic bumpers do not recommend a bake cycle. Once the plastic has cooled, repeat the procedure below for preparing raw plastics beginning with step 2.
- 8. Plastic parts repaired with Permacron 1:1 Elastic Primer Surfacer 3300 may not be washed with a high pressure jet within six weeks of the repair. After this period, the nozzle must be held at a distance of no less than 12 inches from the object.





APPLICATION

SUBSTRATES

All raw plastic parts commonly found on vehicle exteriors (Examples: PP, PP/EPDM, ABS, SAN, PC, PA, PUR-RIM, R-TPU, TPO, PBTP, UP-GF).

Not recommended for pre painted substrates.

SURFACE PREPARATION

Primed Plastic

Perform a solvent test to check if primer is reversible.

- 1. If the primer is reversible, then strip and treat as raw plastic.
- 2. If the primer is not reversible
 - a. Wash with soap and water, clean all substrates thoroughly with:
 - Permaloid[®] Silicone Remover 7087 or 7010 Slow, Permahyd Silicone Remover 7085, or Permahyd Silicone Remover 7096.
 - ii. Axalta™ Silicone Remover 200 Slow, Axalta Silicone Remover 205A Spray, Axalta Silicone Remover 210 Water or Axalta Silicone Remover 220 Low VOC.
 - b. Sand the primer (P500-800 when dry sanding or with P600-800 when wet sanding). Make sure to scuff all of the edges and hard to reach areas with a gray or gold scotch pad.
 - Re-clean with Permaloid Silicone Remover 7087 or 7010 Slow, Permahyd Silicone Remover 7085, or Permahyd Silicone Remover 7096.
 - ii. Axalta™ Silicone Remover 200 Slow, Axalta Silicone Remover 205A Spray, Axalta Silicone Remover 210 Water or Axalta Silicone Remover 220 Low VOC
 - c. Recoat with an elastic Permasolid Surfacer or Sealer.

Raw Plastic

The substrate must be free from release agents.

- Rinse the raw plastic part thoroughly with water and pre-clean it using Permahyd Plastic Cleaning Paste 7081 or Axalta 265 Plastic Cleaning Paste and a clean gold scuff pad.
- Continue to clean the raw plastic part another 2 to 3 times using new Permahyd Plastic Cleaning Paste 7081 or Axalta 265 Plastic Cleaning Paste and a clean gold scuff pad. The supplied brush should be used with Permahyd Plastic Cleaning Paste 7081 or Axalta 265 Plastic Cleaning Paste in hard to reach areas of the plastic part.
- 3. Remove all Permahyd Plastic Cleaning Paste 7081 or Axalta 265 Plastic Cleaning Paste residue from the plastic by thoroughly rinsing with clean water.
- 4. Before further treatment, clean the plastic substrate thoroughly with:
 - Permaloid Silicone Remover 7087 or 7010 Slow, Permahyd Silicone Remover 7085, or Permahyd Silicone Remover 7096.
 - ii. Axalta™ Silicone Remover 200 Slow, Axalta Silicone Remover 205A Spray, Axalta Silicone Remover 210 Water or Axalta Silicone Remover 220 Low VOC.
- 5. Apply Permacron 1:1 Elastic Primer Surfacer 3300 as per below and recoat with Permacron Base Coat Series 293/295 or Permahyd® Hi-TEC 480.



SPRAYGUN SETUP

HVLP 1.3-1.4mm Approved Transfer Efficiency 1.2-1.3mm

Please refer to gun manufacturer and local legislation for proper spray pressure recommendations.

APPLICATION

Apply 1.5 coats (one tack coat followed by one full coat to obtain opacity).

RECOMMENDED FILM THICKNESS

Approximately 1.2 mil dry film thickness



DRY TIMES

AIR DRYING

Drying time at 68°F/20°C: 15-20 min. or max. 8 hrs. prior to Permacron

Base Coat Series 293/295

20-30 min. prior to Permahyd® Hi-TEC 480

2 hours prior to sanding

LOW BAKE

Drying time at 140°F/60°C metal temp.: 30 minutes

WET SANDING

Initial sanding: P320 Final sanding: P600 – 800

RECOAT

With Permacron Base Coat Series 293/295 or Permahyd® Hi-TEC 480



PHYSICAL PROPERTIES

Coating Category: Primer

Max. VOC (AP): 662 g/l; 5.5 lbs/gal Max. VOC (LE): 662 g/l; 5.5 lbs/gal

Avg. Gallon Weight: 1048.1 g/l; 8.75 lbs/gal

Avg. Weight % Volatiles: 63.2% Avg. Weight % Water: 0.0%

Avg. Weight % Exempt Solvent: 0.0% Avg. Volume % Water: 0.0% Avg. Volume % Exempt Solvent: 0.0%

Theoretical Coverage @ 1 mil: 378.5 sq/ ft.

Theoretical Coverage @ Recommended Film Build: 252 sq/ ft.

VOC REGULATED AREAS

These directions refer to the use of products which may be restricted or require special mixing instructions in VOC regulated areas. Follow mixing usage and recommendations in the VOC Compliant Products Chart for your area.



SAFETY AND HANDLING

For industrial use only by professional, trained painters. Not for sale to or use by the general public. Before using, read and follow all label and MSDS precautions. If mixed with other components, mixture will have hazards of all components.

Ready to use paint materials containing isocyanates can cause irritation of the respiratory organs and hypersensitive reactions. Asthma sufferers, those with allergies and anyone with a history of respiratory complaints must not be asked to work with products containing isocyanates.

Do not sand, flame cut, braze or weld dry coating without a NIOSH approved air purifying respirator with particulate filters or appropriate ventilation, and gloves.

Any analytical results set forth herein do not constitute a warranty of specific product features or of the product's suitability for a specific purpose. All products are sold pursuant to our general conditions of sale. We hereby disclaim all warranties and representations, express or implied, with respect to this product, including any warranty of merchantability or fitness for a particular purpose. This product is protected by patent law, trademark law, copyright law, international treaties and/or other applicable law. All rights reserved. Unauthorized sale, manufacturing or use may result in civil and criminal penalties

Revised: September 2019

In the United States: In Canada: 1.855.6.AXALTA | 1.800.668.6945 spieshecker.us | spieshecker.ca

