



Priomat® Wash Primer 4075



GENERAL

DESCRIPTION

Priomat® Wash Primer 4075 is a two-component adhesion promoter from our “PVB-System” that promotes adhesion and serves as passive pretreatment of metal substrates, especially aluminum and top-grade steel. It must be used as part of a three-layer system.

The products referenced herein may not be available for sale in your market. Please consult your distributor for product availability.



MIXING

COMPONENTS

Priomat Wash Primer 4075

PRIOMAT HARDENER

Priomat Activator 4076

MIX RATIO

Component	Volume
4075	1
4076	1

APPLICATION VISCOSITY

15 - 16 seconds at 68°F/20°C, DIN 4

POT LIFE

Approximately 8 hours at 68°F/20°C.

SPECIAL TIPS

- 0.3 mil dry film thickness is necessary for adequate corrosion resistance.
- All traces of rust must be removed before applying Priomat Wash Primer 4075.
- Do not recoat with polyester or epoxy products.
- Do not use on reversible finishes.
- We recommend the following three-layer system:
 - Prime with Priomat Wash Primer 4075.
 - Apply Permasolid® Surfacer or Sealer.
 - Apply Topcoat.
- Metal substrates must be primed within one half-hour of sanding or re-sanding is required.**
- Must be over coated within 8 hours for moisture protection.**



APPLICATION

SUBSTRATES

Properly prepared Bare Steel
 Properly prepared Galvanized Steel
 Properly prepared Aluminum
 Cut throughs on Sanded E-Coat
 Cut throughs on original or old paintwork (except reversible substrates, Example: lacquer)



SURFACE PREPARATION

- Degrease and sand.
- Prior to applying a sanding surfacer, sand body filler with P180 or finer grit sandpaper and/or sand feather edge areas with P180, then P240, and finish with P320.
- Before further treatment, clean all substrates thoroughly with:
 - Permaloid® Silicone Removers 7087 or 7010 Slow, Permahyd® Silicone Removers 7085, 7086 or 7096.
 - Axalta™ Silicone Remover 200 Slow, Axalta Silicone Remover 205A Spray, Axalta Silicone Remover 210 Water or Axalta Silicone Remover 220 Low VOC.

SPRAYGUN SETUP

HVLP 1.3-1.4mm
 Approved Transfer Efficiency 1.2-1.3mm

Please refer to gun manufacturer and local legislation for proper spray pressure recommendations.

APPLICATION

- Option 1: Apply 1 medium coat followed by 1 full coat without intermediate flash-off.
- Option 2: Apply 2 coats with approximately 5 minutes intermediate flash-off between coats.

RECOMMENDED FILM THICKNESS

0.3 mil dry film thickness



DRY TIMES

AIR DRYING

Drying time at 68°F/20°C: 30 minutes

RECOAT

With Permasolid Surfacer or Sealer



PHYSICAL PROPERTIES

Coating Category: Primer
 Max. VOC (AP): 757 g/l; 6.3 lbs/gal
 Max. VOC (LE): 764 g/l; 6.4 lbs/gal
 Avg. Gallon Weight: 924.7 g/l; 7.7 lbs/gal
 Avg. Weight % Volatiles: 82.9%
 Avg. Weight % Water: 1.1%
 Avg. Weight % Exempt Solvent: 0.0%
 Avg. Volume % Water: 0.1%
 Avg. Volume % Exempt Solvent: 0.0%

Theoretical Coverage: 145.6 sq. ft. @ 1 mil
 Theoretical Coverage @ Recommended Film Build: 485 sq. ft.

VOC REGULATED AREAS

These directions refer to the use of products which may be restricted or require special mixing instructions in VOC regulated areas. Follow mixing usage and recommendations in the VOC Compliant Products Chart for your area.



SAFETY AND HANDLING

For industrial use only by professional, trained painters. Not for sale to or use by the general public. Before using, read and follow all label and SDS precautions. If mixed with other components, mixture will have hazards of all components.

Ready to use paint materials containing isocyanates can cause irritation of the respiratory organs and hypersensitive reactions. Asthma sufferers, those with allergies and anyone with a history of respiratory complaints must not be asked to work with products containing isocyanates.

Do not sand, flame cut, braze or weld dry coating without a NIOSH approved air purifying respirator with particulate filters or appropriate ventilation, and gloves.

Any analytical results set forth herein do not constitute a warranty of specific product features or of the product's suitability for a specific purpose. All products are sold pursuant to our general conditions of sale. We hereby disclaim all warranties and representations, express or implied, with respect to this product, including any warranty of merchantability or fitness for a particular purpose. This product is protected by patent law, trademark law, copyright law, international treaties and/or other applicable law. All rights reserved. Unauthorized sale, manufacturing or use may result in civil and criminal penalties.

Revised: September 2019

In the United States: In Canada:
1.855.6.AXALTA | 1.800.668.6945
spieshecker.us | spieshecker.ca

